


# DINITROL 8520

## Rallye AC Satin

### Laquer Spray Black, semi-gloss

DINITROL 8520 Rallye AC Satin Spray black semi-gloss is a quick-drying acrylic lacquer with high opacity.

- » Black dull
- » Decorative and semi-gloss coloured protection (small areas)
- » Fast curing
- » Touch-dry in 20 – 30 minutes (20°C)
- » Easy to use and fast further processing



#### Equipment

**DINITROL Industrial Nitrile Gloves XL**  
Art. No. 1734100

#### DINITROL 8520 Rallye AC Satin

Art. No.	Size	Package	Color
14087	400 ml	Spray can	black dull

# DINITROL 8520 Rallye AC Satin

## Technical Details

### Product Description

DINITROL 8520 Rallye AC Satin Spray black semi-gloss is a quick-drying 1-c acrylic lacquer with high opacity.

### Application

DINITROL 8520 Rallye AC Satin Spray is used in vehicle sector, industry, household. Partial lacquering of metallic surfaces such as iron and non-ferrous metals, plastics, ceramics, wood, etc. New paintwork on goods vehicle steel rims.

Before use, shake the can (1 – 2 mins) until the mixing ball can clearly be heard. Apply the material in an even cross coat. For small surfaces, the product can also be sprayed in a circular movement. The product should be sprayed at a distance of 20 – 30 cm. In order to prevent any blockages, hold the can downwards after use and briefly spray pure gas. Depending on temperature, humidity and coat thickness, the product is touch-dry after approx. 20 – 30 minutes.

### Pre-Treatment Substrates

The substrate must be clean and free from grease, dust and rust. Old and cracked paints must be removed. Lacquer and paint residue in good condition must be matt burnished. In the case of absorptive substrates, such as wood, a pore filler must be applied beforehand in order to prevent lacquer binding agent from spreading to the substrate. A fine spray lacquer pre-coat can also be applied to seal absorptive surfaces.

For additional information, please consult DINOL GmbH.

## Technical Data

Colour	black
Base	Acrylic resin
Density	0,78 g/cm <sup>3</sup>
Flash point	< - 10°C
Drying time (touch dry at 20°C)	approx. 20 min. / 50 µ
Recommended working temperature	17 – 25°C
Propellant	propane / butane
Storage	cool and dry
Storage time	24 months
Cleaning	NC thinner or acrylic thinner
Available in	400 ml spray can

### Hazards identification

#### 2.1. Classification of the substance or mixture

GB CLP Regulation

Aerosol 1; H222-H229; Eye Irrit. 2; H319; STOT SE 3; H336

**For all relevant safety advices please read the material safety data sheet or the packaging label.**