

DINITROL 8530

Rallye AC Brilliant

Laquer Spray Black, high gloss

DINITROL 8520 Rallye AC Satin Spray black, high-gloss is a quick-drying acrylic lacquer with high opacity. The material is extremely weather-resistant.

- » Black gloss
- » Decorative and black gloss coloured consistent protection (small areas)
- » Fast curing
- » Touch-dry in 20 – 30 minutes (20°C)
- » Easy to use and fast further processing



Equipment

DINITROL Industrial Nitrile Gloves XL
Art. No. 1734100

DINITROL 8530

Acrylac Satin

Art. No.	Size	Package	Color
14089	400 ml	Spray can	Black gloss

DINITROL 8530 Rallye AC Brilliant

Technical Details

Product Description

DINITROL 8530 Rallye AC Satin Brilliant black high gloss is a quick-drying 1-c acrylic lacquer with high opacity. The material is extremely weather-resistant.

Application

DINITROL 8530 Rallye AC Brilliant Spray is used in vehicle sector, industry, household. Partial lacquering of metallic surfaces such as iron and non-ferrous metals, plastics, ceramics, wood, etc. New paintwork on motor vehicle steel rims.

In the case of absorptive substrates, such as wood, a pore filler must be applied beforehand in order to prevent lacquer binding agent from spreading to the substrate. A fine spray lacquer pre-coat can also be applied to seal absorptive surfaces.

Before use, shake the can (1 – 2 mins) until the mixing ball can clearly be heard. Apply the material in an even cross coat. For small surfaces, the product can also be sprayed in a circular movement. The product should be sprayed at a distance of 20 – 30 cm.

In order to prevent any blockages, hold the can down-

wards after use and briefly spray pure gas. Depending on temperature, humidity and coat thickness, the product is touch-dry after approx. 20 – 30 minutes.

Pre-Treatment Substrates

The substrate must be clean, free of grease, dust and rust.

Over-Coating

Old and cracked paints must be removed. Healthy residual lacquers should be sanded matt. For additional information, please consult DINOL GmbH.

Technical Data

Colour	black
Base	Acrylic resin
Density	0,76 g/cm ³
Flash point	< - 20°C
Drying time (touch dry at 20°C)	approx. 20 min. / 50 µ
Recommended working temperature	17 – 25°C
Propellant	propane / butane
Storage	cool and dry
Storage time	24 months
Cleaning	NC thinner or acrylic thinner
Available in	400 ml spray can

Hazards identification

2.1. Classification of the substance or mixture

GB CLP Regulation

Aerosol 1; H222-H229; Eye Irrit. 2; H319; STOT SE 3; H336

For all relevant safety advices please read the material safety data sheet or the packaging label.